



Moisture Products Comparison Chart

VAPORSEAL-HM

CUTDOWN II

SUBFLOOR COVER

New (7 day) concrete slabs	✓	NO
Over Plywood subfloor	NO	NO
Cutback or other adhesive residues	NO	✓
Oil contamination	NO	NO

SURFACE PREPARATION REQUIRED

Surface contaminants	Remove All	See Data Sheet (surface preparation)
Profile required	CSP-3	NO
Surface required	Open, Absorptive	Bondable
Surface application condition required	Dry to Slightly Damp	Dry to Slightly Damp

PRODUCT FEATURES

Base material	Epoxy	Latex
For RH Readings up to: (ASTM 2170)	100%	90% (1)
Max. previous emission rate (ASTM #F1869)	25 lbs.	15 lbs (1)
Adhesive compatibility	Excellent	Excellent
Coats required	1	2 to 3
Coverage Rate-Per Unit (sq. ft. per gallon)	70	2 coats-540 (135) 3 coats-360 (90)
Work time (70°-73°F)	15-25 mins	30-40 minutes
Re-coat time (70°-73°F)	-	2-24 hours
Cover time	Within 3 days	Minimum 24-48 Hours
Warranty	10-Year Full Warranty	5 Year Floor Replacement Warranty Available

LEED FEATURES

VOC Content (G/L)	0	0
-------------------	---	---

(1) Two Coat Application (Less than 85% Relative Humidity or 8 lb. MVER)

Three Coat Application (Where may ever exceed 85% RH or 8 lb. MVER)

Allow to dry 2 hours before applying second or third coats. Must read installation instructions prior to application of Cutdown II

P 800 | 227 | 3434

P 440 | 333 | 1123

F 440 | 333 | 0070

www.floorprep.com

