



Dependable, LLC

P.O. Box 241354 • Mayfield Heights, OH 44124 • Tel 800-227-3434 • Fax 440-333-3781

Technical Bulletin SFES-2-99

Aggregate with SKIMFLOW[®] ES

Dependable SKIMFLOW[®] ES may be extended with aggregate by following the steps outlined below. Aggregate shall be a maximum of 3/8" mix. Ratio shall be 3 parts powder, 1 part aggregate (18-20 lbs. aggregate per 55 lb. bag SKIMFLOW[®] ES)

1. Use a clean mixing container. Pour in proper amount of clean cool water and add powder slowly. Water/powder ration is 6 1/2 qt. water to 55 lb. bag of powder.
2. Mix with 1/2" drill at 150 to 450 RPM using a paddle designed to avoid air entrapment. Mix a minimum of 2 minutes.
3. Slowly add proper amount of aggregate while mixing. Ensure aggregate is completely coated.

Mix may be less flowable which may require additional working. A neat layer may be needed to ensure a smooth flat surface. If a second application is necessary, allow the first application to dry, then prime and apply second application following printed instructions.

If you have any questions or comments with respect to this technical bulletin, please contact technical service at Dependable, LLC at 1-800-227-3434.