



MULTI-FAMILY UNDERLAYMENT

GSL® K2.6

Standard Gypsum Underlayment



DESCRIPTION

GSL® K2.6 gypsum cement is an underlayment designed to provide code compliance in wood and concrete UL fire rated assemblies. It is listed on numerous UL designs and has been shown in laboratory testing to provide compliance with IBC standards in impact noise (IIC, ASTM E492) and airborne noise (STC, ASTM E90).

Pumpable, GSL delivers high strength, good water resistance and outstanding performance when placed after drywall in typical multi-family projects. GSL allows for light foot traffic shortly after placement.

Applications from 0.375" up to 3" depth can be achieved in a single pour. GSL remains placable for nearly 30 minutes, yet will withstand light foot traffic at any depth in about 90 minutes. This product offers high density, yet has less finished weight and more flexibility than portland cement self-levelers. Unlike portland cement, gypsum does not shrink and requires no hand finishing tools other than a darby that establishes thickness and uniformity. Typically installed with a specialty mixing machine capable of placing 20,000 to 30,000 square feet per day. GSL K2.6 is specially formulated to add mass to a floor ceiling assembly and help control airborne noise.

GSL is UL approved on all standard assemblies providing developers the fire safety assurance required in today's multi-family projects.

GSL is designed for installation by trained contractors from DEPENDABLE, LLC. Please consult with a local representative for a list of contractors in a specific geography.

APPLICATIONS

- Multi-family
- Light commercial
- Commercial/retail/office
- Hotel/motel
- Assisted living/senior care
- Sound and fire control applications

UL LISTINGS

L501, L502, L503, L504, L505, L506, L507, L508, L509, L510, L511, L512, L513, L514, L515, L516, L517, L518, L519, L520, L522, L523, L524, L525, L526, L527, L528, L529, L530, L534, L535, L536, L537, L538, L539, L540, L541, L542, L543, L546, L547, L549, L550, L551, L552, L556, L558, L560, L563, L570, L574, L576, L577, L581, L583, L585, L587, L588, L590, L592, M500, M503, M504, M508, M511, M512, M517, M530, M535, G577, G578, G579, G580, G581, G582

If your listing is not shown here, please contact Dependable, LLC.

PACKAGING

- GSL K2.6
- 80 lb. (36 kg.) Bag, valve double wall bag

CHARACTERISTICS

Flow Properties:

Medium Flow with Self-Healing Properties

Water Per Bag:

4.0 - 6.0 US GAL per 80 lb. Bag

Final Set Time:

2 hours

Compressive Strength:

2000 - 3500 psi ASTM C472

Sand Per Bag:

1.4 - 2.1 cu. ft. of washed plaster or concrete sand
(Meeting Dependable, LLC Gradation Criteria)

Thickness Range:

0.375" - 3.0" poured in single lift. Minimum 3/4"
depth over all wood substrates.

Surface Burning: ASTM E84

Flame Spread: 0

Fuel Contribution: 0

Smoke Density: 0

Wet Density (with aggregate):

135 - 150 lbs./cu.ft.

Dry Density (with aggregate):

110 - 125 lbs./cu.ft.

Color: Gray Powder and mixed to a gray batter consistency

FEATURES AND BENEFITS

- Provides additional protection for fire resistance as shown in UL approved assemblies
- Provides additional sound control enhancements as tested under ASTM E90, Airborne Noise or STC and ASTM E492, Impact Noise or IIC
- Pourable over virtually any surface (especially plywood and OSB subfloors)
- Durable high strength gypsum
- Outstanding heal that provides a smooth, dense surface
- Open time up to 30 minutes
- Non-Alkaline—adhesive friendly
- Can pour up to 3" in a single lift
- Withstands construction but should be protected when exposed to trade traffic or wheeled loads
- As little as 3/8" coverage over other surfaces

PREPARATION AND APPLICATION

SITE CONDITIONS

- Building must be fully enclosed including doors, windows and roof.
- Interior ambient temperature must be 50°F at least one day before installation and maintained at "a minimum of" 50°F temperature for a minimum of 4 to 5 days after installation.
- Adequate ventilation must be maintained until the moisture in the gypsum has been allowed to evaporate. This requirement is typically a minimum of 5 to 7 days, but may be longer depending on thickness of underlayment, humidity and conditions in the local environment.
- Subfloor must be a minimum of L/360, broom swept with all excess wall board mud removed and all holes patched.
- Wood construction must be with tongue and groove subfloor (OSB or plywood).
- For installation on concrete substrates the subfloor must be fully cured (minimum 28 days). Moisture tests should be performed to assure proper hydration under ASTM F1869 to assure MVE level is less than 3.0 lb. per 1000 square feet.
- For below grade applications or over a crawl space, vapor barriers must be applied.

SUBFLOOR PREPARATION

Subfloor must be properly primed. Use GSL PRIMER on all surfaces. Approved priming methods include: roller, soft bristle broom, brush or spray. All supporting surfaces shall be structurally sound, solid, free of movement and well bonded. They shall be dry, free of dust, oil, grease, tar or other contaminants that may act as a bond breaker. Deflection cannot exceed L/360.

Priming

Dilute GSL Primer before application. Dilute 1 part GSL PRIMER concentrate to 4 parts potable water (1:4). Using a long handle roller, soft bristle broom, brush or sprayer, apply GSL PRIMER at a coverage rate of 270-320 sq. ft. per gallon of primer solution. Coverage rate varies depending upon surface porosity. Ensure a complete and uniform coverage. Allow to become very tacky or dry (about 1 hour).

Mixing

Follow DEPENDABLE, LLC guidelines and specifications. GSL is only to be installed by trained contractors approved by Dependable, LLC.

MIXING INSTRUCTIONS

Type	*Mix Design (Cubic feet sand/)	*Water (gal)	Slump (Inches)
K2.6	1.4 - 2.1	4.0 - 6.0	9" ± 1-inch

* Sand and Water per 80 Lb. bag

24 HOUR EMERGENCY: CHEMTREC® 1-800-424-9300 NON-TOXIC and NON-FLAMMABLE

Keep container closed and keep away from children. May cause slight eye abrasion or irritation if spilled or rubbed in eyes. Flush thoroughly with water.

If taken internally, call a physician. Technical Assistance:
Visit our website: floorprep.com or call 1-800-227-3434.

Compressive Strength

2000 - 3500 psi

Substrate

Plywood, OSB, concrete, precast concrete and approved acoustical treatment are acceptable. Wood substrate must be proper thickness, tongue and groove construction and properly fastened. Concrete should be clean, dry and free of obvious structural problems. All substrates must be properly sealed and/or primed before the GSL floor underlayment is applied.

Storage

Material should be kept in a dry area. Avoid ambient temperature below 50°F and above 110°F for prolonged periods. Shelf-life of six months.

APPLICATION

- **Multiple lifts:** Multiple lifts may not require a primer with GSL. Second lift can be accomplished upon an initial set that can handle the load of the hose operator and finisher.

NOTE: Temperature and humidity levels affect the drying characteristics of GSL. However, unlike Portland cement materials, GSL may be force dried with the use of heat or fans once set.

LIMITATIONS / PRECAUTIONS

- DO NOT USE IN EXTERIOR APPLICATIONS. For Interior use only.
- GSL is NOT a wear surface.
- DO NOT INSTALL WITHOUT TONGUE AND GROOVE SUBFLOOR unless utilizing back bracing or filling all joints.
- CHECK JOIST DEFLECTION and assure performance greater than L/360
- ASSURE BUILDING IS COMPLETELY INCLOSED including doors, windows and roof.
- INSTALLATION TEMPERATURE MUST BE 50°F and rising.
- PROVIDE ADEQUATE VENTILATION after placement of GSL until dry.

DO NOT USE...

- Where hydrostatic pressure (water) is present or moisture emissions exceeds level permitted for installed floor covering.
- Where surface or ambient temperature falls to or below 50°F 72 hours before or after installation.
- As a trowelled patch or at less than natural minimum flow thickness.
- Exterior, exposed applications or as a wear surface.

LIMITED WARRANTY:

Dependable, LLC warrants to the initial purchaser only that the goods sold hereunder will be free from defects in material and workmanship and, except as otherwise set forth herein, will conform to the specifications provided. If any failure to meet this warranty appears within one year from the date of shipment of the goods, on the condition that Dependable, LLC. will correct any such failure by either replacing or repairing any defective goods, at Dependable, LLC's option.

The preceding paragraph sets forth the exclusive remedy for all claims based on failure of or defect in the goods sold hereunder, whether such failure or defect arises before or during the warranty period and whether a claim, however instituted, is based on contract, indemnity, warranty, tort (including negligence), strict liability or otherwise. The forgoing warranty is exclusive and is in lieu of all other warranties whether written, oral, implied or statutory.



info@dependable.us
floorprep.com

800 | 227 | 3434
P 440 | 333 | 1123
F 440 | 333 | 3781

2018/1
2/2