

SKIMCRETE® PRU (PRONTO ULTRA™)**DESCRIPTION**

PRONTO ULTRA™ is a fast setting/ fast drying latex modified gypsum based floor underlayment patch. It is used to patch or fill interior wood, above, below or on grade concrete substrates.

PRONTO ULTRA offers compressive strength of 3,000 psi., is moisture resistant and mold/mildew resistant.

PRONTO ULTRA may be used from feather edge to 1/2" thickness.

FEATURES AND BENEFITS

- Fast Setting / fast drying
- Creamy, grit free
- Good finishability

PACKAGING

- 25 lb (11.3 kg) double wall bag

PHYSICAL CHARACTERISTICS

Working Time: About 10 minutes

Setting Time: 35 minutes

Covering Time: 30-75 minutes

Compressive Strength: 3000 psi

Flexural Strength: 1000 psi

Coverage (in square feet per 100 lbs.):

Thickness (in)	1/32	1/16	1/8	1/4	1/2	3/4	1
----------------	------	------	-----	-----	-----	-----	---

Coverage (sq.ft.)	592	296	148	73.8	36.9	24.6	18.5
-------------------	-----	-----	-----	------	------	------	------

25 lb. Bag covers 74 sq. ft. at 1/16" thickness

Thickness: Feather edge to 1/2" (neat)

Mix Ratio: 2-1/2 parts powder to 1 water

Application Conditions: Interior above 50°F (10°C)

Color: Gray

All specifications were tested in laboratory conditions: 70° in a controlled environment using our approved water content. Changing the temperature, or mixing ratios, or the environment can effect these specifications. Call Technical Services if you have any questions.

LEED CREDIT

AREA	CREDIT	CATEGORY	HOW
Indoor Environmental Quality	EQ 4.2	Low Emitting Materials	Zero VOC
Materials and Resources	MR 4.1-4.2	Recycled Content	25%
	MR 5.1	Regional Manufactured Material	Cleveland, OH
	MR 5.2	Regional Materials	6%

PREPARATION AND APPLICATION**SURFACE PREPARATION**

All supporting surfaces shall be structurally sound, solid, free of movement and well bonded. Make sure underlying surface is free of moisture and clean of any contaminants such as dirt, solvent, wax, paint, sealers, adhesive, chemical residue, oil products, or any other foreign matter that interferes with bond. In any application where adhesion is in doubt, perform a test patch in an inconspicuous area. Do not proceed if dissatisfied with bond and contact Technical Assistance.

Concrete Floors

Remove all foreign matter by mechanical means. Floor must be free of efflorescence and excess moisture. To check moisture, test with a calcium chloride test (ASTM F1869), or relative humidity (insitu probe) test (ASTM F2170). To correct moisture problems, see DEPENDABLE's moisture protection products.

PREPARATION AND APPLICATION Continued

Wood Floors

Ensure wood floors are free of excessive moisture and well supported. Fasten any loose boards. Stripwood floors should be covered with underlayment board.

Underlayment Board Joints

To avoid peaking, do not butt sheets tightly. Leave a space the thickness of a matchbook cover (approx. 1/32") between sheets. The installer may wish to seal the joints, hammer-indent and any other "raw" spots with an appropriate "brush coat" or DEPENDABLE WHITE LATEX LIQUID®. This will keep the moisture in PRONTO ULTRA and/or the adhesive from being drawn into the board, which may cause swelling and/or delamination.

MIXING

Per 25 lb bag PRONTO ULTRA use 5 quarts cool, clean water or about 2.5 parts powder to 1 part water. Use clean containers and mixing implements, as leftover residue can accelerate set and/or reduce pot life of new mix. Mix thoroughly to a lump-free trowelable consistency. Mixture will remain workable for 10 minutes. Mix only what can be used in that time. Do not attempt to extend pot life by later adding water. Do not mix directly on floor. Use felt, scrap vinyl or mixing bucket.

APPLICATION

Using a notchless trowel, force PRONTO ULTRA into joints, cracks, voids and deeper fills bearing down on the trowel, then smooth a thin covering over the prepared substrate and build any thicker fills or transitions to over 1 inch thick. Allow the PRONTO ULTRA to dry thoroughly before going over the surface with a second application if needed. When dry, scrape or sand smooth for a perfect finish.

LIMITATIONS

Do not use...

- Where hydrostatic pressure (water) is present or moisture emissions exceeds level permitted for installed floor covering. PRONTO ULTRA can tolerate any amount of moisture from a concrete slab so long as all of the moisture from the slab will escape past the floor covering. If the floor covering's moisture permeability does not meet or exceed the moisture content of the slab, Dependable recommends moisture remediation. Use Dependable's Vaporseal HM, or an approved alternative, to remediate moisture in concrete, consult the Vaporseal HM data sheet, or call technical services, for more details.
- When surface or ambient temperature falls to or below 45°F within 72 hours of installation.
- Over presswood, particle board, masonite, chip-board, OSB, underlayment board not of APA Underlayment (exterior) grade or similar dimensionally unstable materials susceptible to movement or swelling.
- Over single layer stripwood floors.

24 HOUR EMERGENCY: CHEMTREC® 1-800-424-9300 NON-TOXIC and NON-FLAMMABLE

Keep container closed and keep away from children. May cause slight eye abrasion or irritation if spilled or rubbed in eyes. Flush thoroughly with water. If taken internally, call a physician.

If taken internally, call a physician. Technical Assistance:
Visit our website: floorprep.com or call 1-800-227-3434.

LIMITED WARRANTY:

Dependable, LLC warrants to the initial purchaser only that the goods sold hereunder will be free from defects in material and workmanship and, except as otherwise set forth herein, will conform to the specifications provided. If any failure to meet this warranty appears within one year from the date of shipment of the goods, on the condition that Dependable, LLC. will correct any such failure by either replacing or repairing any defective goods, at Dependable, LLC's option.

The preceding paragraph sets forth the exclusive remedy for all claims based on failure of or defect in the goods sold hereunder, whether such failure or defect arises before or during the warranty period and whether a claim, however instituted, is based on contract, indemnity, warranty, tort (including negligence), strict liability or otherwise. The foregoing warranty is exclusive and is in lieu of all other warranties whether written, oral, implied or statutory.



info@dependable.us
floorprep.com

800 | 227 | 3434
P 440 | 333 | 1123
F 440 | 333 | 3781