

## SECTION 03 54 00 – Cast Underlayment SECTION 09 80 00 – Acoustic Treatment



### Guide Specification for GSL K2.6

---

#### PART I – GENERAL

##### 1.01 SUMMARY

- A. Description: This section includes underlayment for interior finish flooring and is not limited to the following:
1. Application on Dependable LLC's GSL K2.6 gypsum-based poured underlayment.
  2. Division 3 Section-Concrete: "Cast Underlayment" and "Gypsum Cement Underlayment"
  3. Division 9 Section-Finishes: "Acoustic Treatment"

##### 1.02 SUBMITTALS

- A. Product Data: Submit product data sheets GSL K2.6 floor underlayment, Quiet Qurl sound mat and installation instructions with project materials clearly identified for each required product or system.
- B. UL Directory Fire Resistance Volume 1 (Choose from Listing)
1. L501, L502, L503, L505, L506, L508, L509, L511, L512, L513, L514, L515, L516, L518, L519, L522, L523, L524, L525, L526, L528, L529, L530, L536, L541, L543, L546, L547, L550, L551, L552, L556, L557, L558, L560, L563, L564, L565, L574, L576, L579, L581, L583, L585, L587, L588, L592, M500, M503, M504, M508, M511, M512, M514, M515, M517, M518, M528
  2. For more info please see UL Certification Database ([ul.com/database](http://ul.com/database))
- C. Acoustical Data: Submit sound tests according to IBC code criteria ASTM E492 (IIC) and ASTM E90 (STC) or ASTM E1007 (F-IIC) and E336 (F-IIC). Contact Keene Building Products for Specifics.
- D. Code Approvals: See <http://www.keenebuilding.com> for the current list of code approvals.

##### 1.03 SYSTEM REQUIREMENTS

- A. Performance Requirements:
1. GSL K2.6 floor underlayment
    - i) Compressive strength 2,000 to 3,500 psi
    - ii) Dry Density 110-125 pounds per cubic foot

Potential USGBC LEED Credit Contribution:

1. MR Credit 3: Building Product Disclosure and Optimization - Sourcing Raw Material
  2. EQ Credit 2: Low Emitting Materials.
- Contact Dependable, LLC for specific details.

2. Sound Control – 2009 International Building Code: Section 1207.2 & .3
  - i) Minimum Sound Transmission Class, 50 STC (45 if field tested) – Section 1207.2
    - (1) ASTM E90 and E336
  - ii) Minimum Impact Insulation Class, 50 IIC (45 if field tested) – Section 1207.3
    - (1) ASTM E492 and E1007

##### 1.04 QUALITY ASSURANCE

- A. Performance Standards:
- Contractor shall be knowledgeable and well trained in the use of floor underlayment material.
1. Underlayment mix shall be tested for a slump using a 2" (i.d.) x 4" (50 mm x 101 mm) cylinder resulting in a patty size of 9" (228 mm) plus or minus a 1-inch (25 mm) diameter.
  2. Compressive strength tested in accordance with ASTM C 472M.

## 1.05 DELIVERY, STORAGE AND HANDLING

- A. Comply with manufacturer's instructions. Deliver in original, unopened packaging. Store in dry conditions and protect from direct sun exposure, freezing, and extreme heat (greater than 105°F (41°C)).

## 1.06 PROJECT CONDITIONS

- A. Before, during and after installation of product, building interior shall be enclosed, with adequate ventilation and heat maintained at a temperature above 50°F (10°C) to allow for drying of product.

## PART 2 – PRODUCTS

### 2.01 PRODUCTS AND MANUFACTURERS

- A. Manufacturer: Dependable, LLC, Rocky River, OH. Phone: (800) 227-3434.
- B. Quiet Qurl Sound Mat: Keene Building Products, Mayfield Heights, OH. Phone (877) 514-5336.

### 2.02 MATERIALS

- A. Proprietary products/systems: Poured flooring underlayment and topping products, including the following:
  1. GSL K2.6 Floor Underlayment
- B. Proprietary products/systems: Optional Sound Control that does not negate the fire rating and is specified in UL design. Acoustical performance is dependent on system design and construction. Please consult Keene Building Products for recommendation if needed.
  1. Quiet Qurl® 52/013 MC, RF, or MC MT Sound Mat
  2. Quiet Qurl® 55/025 MC, RF, or MC MT Sound Mat
  3. Quiet Qurl® 60/040 MC, RF, or MC MT Sound Mat
  4. Quiet Qurl® 65/075 MC, RF, or MC MT Sound Mat
- C. Dependable, LLC Floor Primer:
  1. Material Standard: Comply with specifications outlined in manufacturer's Design and Installation Guide for wood.
- D. Mix Water:
  1. Material Standard: Potable, free from impurities and from a domestic source.
- E. Sand Aggregate:
  1. Sand shall meet Dependable, LLC Sand Specification 101.
- F. Dependable, LLC GSL All Purpose Sealer:
  1. Seal all areas that receive glue down floor goods with Dependable, LLC GSL All Purpose Sealer according to manufacturer's specifications.
- G. Keene Building Products Reinforcement Mat (Optional):
  1. Quiet Qurl RWT 040
    - i) Install approved reinforcement as per manufacturer recommendations.

## PART 3 – EXECUTION

### 3.01 EXAMINATION

- A. Site Verification of Conditions:
  1. Building must be fully enclosed including windows and roof.
  2. Interior ambient temperature must be 50°F and rising at least one day before installation and maintained at "a minimum of" 50°F temperature for a minimum of 4 to 5 days after installation or until dry.
  3. Subfloor must be dry, a minimum of L/360 and broom swept with all excess wall board mud removed, all holes patched.

4. Wood construction must be with tongue and groove subfloor (OSB or plywood).
5. Adequate ventilation must be maintained until the moisture in the gypsum has been allowed to evaporate. This requirement is typically a minimum of 5 to 7 days but may be longer depending on humidity conditions in the local environment.
6. For installation on concrete substrates the subfloor must be fully cured (typically 28 days). Moisture tests should be performed to assure proper hydration using ASTM F1869 to assure MVE level is less than 3.0 lb. per 1000 square feet.
7. For below grade applications or over crawl space in residential, vapor barriers must be applied.

### 3.02 REQUIREMENTS

- A. Surface Preparation:
  1. Subfloor must be properly primed.
  2. Use Dependable, LLC's GSL PRIMER on all surfaces.
  3. All supporting surfaces shall be dry, structurally sound, solid, free of movement and well bonded. They shall be free of dust, oil, grease, tar or other contaminants that may act as a bond breaker.
  4. Deflection cannot exceed L/360.
- B. Priming:
  1. Dilute GSL Primer before application. Dilute 1-part GSL PRIMER concentrate to 4 parts potable water (1:4).
  2. Using a long handle roller, soft bristle broom, brush or sprayer, apply GSL PRIMER at a coverage rate of 270-320 sq. ft. per gallon of primer solution.
  3. Ensure a complete and uniform coverage.
  4. Allowed to become very tacky or dry (about 1 hour).

### 3.03 GENERAL INSTALLATION REQUIREMENTS

- A. Mixing Proportions:
  1. General Requirements: Mix proportions and methods shall be in strict accordance with product manufacturer recommendations.
- B. Application:
  1. (Optional) Quiet Qurl Installations: Install Quiet Qurl following manufacturer's recommendations and specifications.
  2. Pour floor topping to recommended thickness. Immediately spread and screed product to a smooth surface. Expansion joints in all types of work shall be brought through the underlayment.
    - i) Minimum Keene Building Products Underlayment Depth:

| <b>Mat Thickness 0.125 Inches / 3.0 mm</b> |            |         |             |
|--|------------|---------|-------------|
| <b>Quiet Qurl 52/013 MC</b>                | 0.75 inch  | 150 ft. | 600 sq. ft. |
| <b>Quiet Qurl 52/013 MC MT</b>             | 0.875 inch | 100 ft. | 400 sq. ft. |
| <b>Quiet Qurl 52/013 RF</b>                | 0.75 inch  | 150 ft. | 600 sq. ft. |
| <b>Quiet Qurl 52/013 RF MT</b>             | 0.75 inch  | 100 ft. | 400 sq. ft. |
| <b>Mat Thickness 0.25 Inches / 6.0 mm</b>  |            |         |             |
| <b>Quiet Qurl 55/025 FT</b>                | 1.0 inch   | 100 ft. | 400 sq. ft. |
| <b>Quiet Qurl 55/025 MC</b>                | 1.0 inch   | 100 ft. | 400 sq. ft. |
| <b>Quiet Qurl 55/025 MC MT</b>             | 1.0 inch   | 50 ft.  | 200 sq. ft. |
| <b>Quiet Qurl 55/025 RF</b>                | 0.75 inch  | 100 ft. | 400 sq. ft. |
| <b>Quiet Qurl 55/025 RF MT</b>             | 1.0 inch   | 50 ft.  | 200 sq. ft. |
| <b>Mat Thickness 0.40 Inches / 10.0 mm</b> |            |         |             |
| <b>Quiet Qurl 60/040 MC</b>                | 1.0 inch   | 100 ft. | 400 sq. ft. |
| <b>Quiet Qurl 60/040 MC MT</b>             | 1.25 inch  | 50 ft.  | 200 sq. ft. |
| <b>Quiet Qurl 60/040 RF</b>                | 1.0 inch   | 100 ft. | 400 sq. ft. |
| <b>Quiet Qurl 60/040 RF MT</b>             | 1.0 inch   | 50 ft.  | 400 sq. ft. |
| <b>Mat Thickness 0.75 Inches / 19.0 mm</b> |            |         |             |
| <b>Quiet Qurl 65/075 MC</b>                | 1.5 inch   | 50 ft.  | 200 sq. ft. |
| <b>Quiet Qurl 65/075 N MT</b>              | 1.5 inch   | 50 ft.  | 200 sq. ft. |
| <b>Quiet Qurl 65/075 N RF</b>              | 1.5 inch   | 50 ft.  | 200 sq. ft. |
| <b>Quiet Qurl 65/075 RF MT</b>             | 1.5 inch   | 50 ft.  | 200 sq. ft. |

\*\*\*Unless otherwise specified in written notice by Keene Building Products\*\*\*

- C. Drying:
1. The general contractor must provide and maintain correct environmental conditions to keep the building clean and dry and protect against infestation of moisture from a variety of potential sources. The general contractor must supply mechanical ventilation and heat if necessary to remove moisture from the area until the GSL K2.6 is dry.
  2. Protection from Heavy Loads: During construction, place temporary wood planking over GSL K2.6 wherever it will be subject to heavy wheeled or concentrated loads.

### 3.04 PREPARATION FOR INSTALLATION OF GLUE DOWN FLOOR GOODS

- A. Sealing:
1. Seal all areas that receive glue down floor goods with Dependable, LLC's GSL All Purpose Sealer according to the Dependable, LLC specifications. Any floor areas where the surface has been damaged shall be cleaned and sealed regardless of floor covering to be used. Where floor goods manufacturers require special adhesive or installation systems, their requirements supersede these recommendations.
- B. Moisture Testing:
1. Follow the respective floor goods manufacturers' recommendations for relative humidity requirements.
- C. Finished Floor Goods:
1. There are many reference standards for the installation procedures and recommendations for finished flooring applications over gypsum underlayments. These include instructions of the manufacturers of the finished flooring, adhesives and thin-set as well as national agency reference standards. The national standards are listed below:

| Flooring Type | Reference Standard |
|---------------|--------------------|
| Resilient     | ASTM F2419         |
| Ceramic Tile  | TCNA F180          |
| Wood          | NWFA Instructions  |

### 3.05 PRECAUTIONS AND LIMITATIONS

- A. Do not use in exterior applications. For Interior use only.
- B. **Do not use:**
1. Where hydrostatic pressure (water) is present or moisture emissions exceeds level permitted for installed floor covering.
  2. Where surface or ambient temperature falls to or below 50°F 72 hours before or after installation.
  3. As a trowelled patch or at less than natural minimum flow thickness.
  4. Exterior, exposed applications or as a wear surface.
- C. GSL is not a wear surface.
- D. Do not install without tongue and groove subfloor unless utilizing back bracing or filling all joints.
- E. Check joist deflection and assure performance greater than L/360
- F. Assure building is completely enclosed, including windows and roof.
- G. Installation temperature must be 50°F and rising.
- H. Provide ventilation after placement of GSL.

END OF SECTION