



Liquid Applied
Waterproofing Membrane

KeedeShield®



KeedeShield® is a fast-drying, liquid-applied membrane that provides waterproofing and crack isolation for tile and stone applications. Designed for walls, floors, and uneven surfaces, it forms a durable moisture barrier by building strong bonds to common surfaces found in commercial and residential construction—indoors and out.



FEATURES

- › Easy to apply with trowel, roller or sprayer
- › Use for Interior surfaces and exterior concrete/masonry surfaces
- › Tile in 60 - 90 Minutes
- › Meets and exceeds the requirements of A.N.S.I. 118.10 and 118.12

SUITABLE APPLICATIONS

- › Between slabs, such as parking decks, roof decks, or courtyard areas over subterranean parking
- › Exterior walls or foundations and basements or other structures that are to be backfilled
- › Inside planter boxes
- › Under terrazzo or tile floors
- › Under shower pans, kitchen, laundry, and bathroom floors.
- › Inside elevated swimming pools or hot tubs.



Easy to use, rapid drying liquid applied waterproofing membrane for crack-isolation and waterproofing applications.

KeedeShield® can be applied to walls, floors, and most irregular surfaces. KeedeShield® is suitable for use on interior or exterior commercial, industrial and residential tile and stone installations. Apply KeedeShield® by roller, trowel or sprayer to create a continuous water and moisture barrier with excellent adhesion. KeedeShield® bonds to metal, PVC, stainless steel and ABS.

Properties		
Drying Time	1-1.5 hours depending on ambient conditions	
Coverage (Per Gallon)	Wet Film Thickness	Approximate Coverage
	20 mils	80 sq.ft/gal
	40 mils	40 sq.ft/gal
	50 mils	32 sq.ft/gal
	60 mils	26.7 sq.ft/gal
	100 mils	16 sq.ft/gal
Shelf Life	18 Months - when stored correctly	
Color	Wet - Navy Blue; Dry - Black.	
SKU	Case of 4 x1G: D-KS-4x1 3.5G Pail: D-KS-3.5	

All specifications were tested in laboratory conditions: 70°F in a controlled environment using our approved water content. Changing the temperature, or mixing ratios, or the environment can effect these specifications. Call Technical Services if you have any questions.



STANDARDS

- › Meets and exceeds the requirements of A.N.S.I. 118.10 and conforms to the requirements of ASTM C-836-89.
- › Meets ANSI 118.12 High Performance (up to 1/8" (3mm) for crack isolation membranes.
- › Meets Uniform Plumbing Code specifications for use as a shower pan liner. Listed with IAPMO R & T, File #4244 UPC®, ICC-ES ESR-1413.
- › Meets low perm requirements for steam room vapor barriers per ASTM E-96 Procedure E

