

General Patch & Skimcoat

# SKIMCRETE® XL



**SKIMCRETE® XL** is a fast-drying, polymer-modified cement patch offering extended working time without delaying your finish. Ideal for most interior surfaces, it provides superior workability, uniform drying, and a creamy, grit-free application with no dusting or cracking.



### **FEATURES**

- Long working time
- Rapid, uniform drying time
- No additives required
- Feather edge to 1" thick
- Superior workability
- Low alkalinity, adhesive friendly
- Creamy, grit-free application
- No dusting or cracking

### **SUITABLE SUBSTRATES**

- Concrete (28 days old)
- Wood (APA Rated)
- Gypsum (primed & sound)



## Fast Drying, Polymer Modified Patch & Skimcoat

**SKIMCRETE**® **XL** is a fast drying, polymer modified, cementitious patch for smoothing dry interior substrates prior to installation of flooring finishes. Fast drying with extended potlife extends your working time, but doesn't delay your finish. **SKIMCRETE**® **XL** is easy to work with on virtually any interior surface.

### **Properties**

Troportios					
Working Time	Approximately 15 minutes				
Set Time	30 minutes				
Covering Time	Approximately 30-75 minutes depending on temperature				FLOOR
Compressive Strength	>4000 psi (28 MPa)				PREP
Coverage (25 lb Bag)	Feather Edge: 110 - 130 sq. ft. 1/8": 25 -35 sq. ft.			Chy	BY DEPENDABLE
Thickness	Feather edge to 1" (25 mm) NEAT	Gun		() à	FEATHER AND PATCH
Mix Ratio	4 qt potable water to 25 lb bag 8 qt potable water to 50 lb bag	S	Polymer Modified Cement Patch		
Application Conditions	Interior above 50°F	SKIMC	SKIMC  Polymer Modified Parche de cemen	X	Fast drying     High Strength     Adhesive Friendly
Color	Gray	CRETE	Fast drying     High Streets	3	Secado rápido     Alta resistencia     Adhesivo amigable
All specifications were tested in laboratory conditions: 70°F in a controlled environment using our approved water content. Changing the temperature, or mixing ratios, or the environment can effect these specifications. Call Technical Services if you have any questions.			Adhesive Fi     Secardo rápi     Alta resisten     Adhesivo an	CRETE	Net Weight 25 ib. (11.3 kg.) Peso Neto 25 lb. (11.3 kg.)
			GROSS WEIGHT 45 lb. (22.6 kg.)	"XL	Dependable, LLC, 800122713434
					floorprep com

Leed Credit SKIMCRETE® XL may contribute to LEED certification of projects as follows:

AREA	CREDIT	CATEGORY	ном
Indoor Environmental Quality	EQ 4.2	Low Emitting Materials	VOC content 0g/I (calculated)
Materials & Resorces	MR 4.1 4.2	Recycled Content	0%
Regional Manufactured Material	MR 5.2	Regional Materials	45%

